



AEP Span Color Performance Data

Please note that color specific CRRC Notification of Product Rating can be produced upon request

PRODUCT DESCRIPTION	CA TITLE 24 & ENERGY STAR						LEED						OTHER			
	via CRRC listings (data based on color families)				Energy Star		CA Title 24	via Accredited Independent Testing Laboratory (using ASTM C1549, C1371, & E1980)								
	CRRC Reference Number	Solar Reflectance (Init.)	Thermal Emittance (Init.)	SRI Init.	Low Slope	Steep Slope		Solar Reflectance (Init.)	Thermal Emittance (Init.)	SRI Init.	Low Slope (Leed V3)	Steep Slope (Leed V3)	Low Slope (Leed V4)	Steep Slope (Leed V4)	LRV	
BARE ZINCALUME®																
ZINCALUME® Plus	1014-0002	0.68	0.30	65	✓	✓		0.68	0.30	64		✓		✓	67	
DURA TECH™ NT COLORS							REFER TO CALIFORNIA ENERGY COMMISSION (CEC) REQUIREMENTS									
CHESTNUT BROWN	0818-0034	0.32	0.83	31		✓		0.35	0.83	36		✓				12
DENALI GREEN	0818-0028	0.25	0.83	22		✓		0.30	0.83	29		✓				11
DESERT BEIGE	0818-0042	0.45	0.83	49		✓		0.51	0.84	58		✓		✓		39
LIGHT STONE	0818-0033	0.55	0.83	63		✓		0.60	0.84	70		✓		✓		53
OLD TOWN GRAY	0818-0039	0.35	0.83	35		✓		0.40	0.84	43		✓		✓		27
RUSTIC RED	0818-0031	0.35	0.83	35		✓		0.40	0.84	43		✓		✓		13
SURF WHITE	0818-0036	0.55	0.83	63		✓		0.63	0.84	74		✓		✓		59
TAHOE BLUE	0818-0027	0.25	0.83	22		✓		0.33	0.84	33		✓				14
WEATHERED COPPER	0818-0035	0.32	0.83	31		✓		0.32	0.83	32		✓				11
WINTER WHITE	0818-0044	0.70	0.83	84	✓	✓		0.73	0.83	88	✓	✓	✓	✓		74
DURA TECH™ 5000 & DURA TECH™ MX COLORS																
COLONIAL RED	0818-0016	0.25	0.83	22		✓		0.34	0.85	35		✓				9
DARK BRONZE	0818-0018	0.25	0.83	22		✓		0.32	0.84	32		✓				8
FOREST GREEN	0818-0012	0.25	0.83	22		✓		0.30	0.84	29		✓				9
LEAF GREEN	0818-0015	0.25	0.83	22		✓	0.30	0.85	30		✓				11	
MATTE BLACK	0818-0046	0.25	0.83	22		✓	0.30	0.84	29		✓				5	
METALLIC CHAMPAGNE	0818-0038	0.35	0.75	32		✓	0.48	0.84	54		✓		✓		33	
METALLIC COPPER	0818-0006	0.35	0.75	32		✓	0.48	0.83	53		✓		✓		29	
METALLIC SILVER	0818-0003	0.35	0.75	32		✓	0.57	0.82	65		✓		✓		50	
MIDNIGHT BRONZE	0818-0055	0.25	0.83	22		✓	0.28	0.84	27		✓				7	
OLD TOWN GRAY	0818-0009	0.35	0.83	35		✓	0.40	0.85	43		✓		✓		27	
PARCHMENT	0818-0047	0.45	0.83	49		✓	0.51	0.84	58		✓		✓		40	
PEBBLE	0818-0059	0.32	0.83	31		✓	0.43	0.85	48		✓		✓		27	
REGAL BLUE	0818-0008	0.25	0.83	22		✓	0.30	0.84	29		✓				10	
REGAL WHITE	0818-0049	0.70	0.83	84	✓	✓	0.73	0.84	88	✓	✓	✓	✓		75	
SAGE GREEN	0818-0056	0.35	0.83	35		✓	0.38	0.84	41		✓		✓		21	
SIERRA TAN	0818-0020	0.45	0.83	49		✓	0.49	0.84	55		✓		✓		34	
SILVERSMITH	0818-0058	0.35	0.75	32		✓	0.52	0.82	58		✓		✓		54	
SLATE GRAY	0818-0057	0.25	0.83	22		✓	0.32	0.85	33		✓				12	
TAHOE BLUE	0818-0007	0.25	0.83	22		✓	0.33	0.84	33		✓				14	
TERRA COTTA	0818-0037	0.35	0.83	35		✓	0.39	0.84	41		✓		✓		15	
VINTAGE®	1014-0003	0.30	0.70	22		✓	0.30	0.70	22						20	
WALNUT	0818-0054	0.32	0.83	31		✓	0.37	0.84	38		✓				18	
WEATHERED COPPER	0818-0019	0.32	0.83	31		✓	0.34	0.83	34		✓				11	
ZACTIQUE® II	0818-0004	0.35	0.75	32		✓	0.37	0.84	39		✓		✓		22	
ZINC GRAY	0818-0010	0.35	0.83	35		✓	0.37	0.85	39		✓		✓		20	

All ratings listed above are initial readings. Three year performance data is located on the CRRC website and is based on CRRC color families.

^A - Reflectivity data for Bare ZINCALUME is actual 3 year weathered solar reflectivity data.