

# Graffiti-Resistant Coating System



## PROTECT YOUR PROJECT FROM GRAFFITI...

Architectural metal siding not only shields a building from nature's elements, it can protect your project from graffiti. AEP Span's factory applied Graffiti-Resistant Coating System is formulated to work with PPG Industries' DuraPrep® Prep 400 graffiti remover.

This innovative coating system includes a primer, a color coat, and a graffiti-resistant clear coat. The clear coating works as a barrier of protection over the color coat layer and prevents most graffiti material from gripping or shadowing the surface. The DuraPrep Prep 400 is applied directly on the graffiti and easily wipes it off of the pre-painted graffiti-resistant coated metal surface.

The graffiti removal system offers building owners an easy and fully tested maintenance method to safely remove graffiti, keeping buildings looking their best.

**Easily removes fresh aerosol paint, overspray, tar, crayon, printing ink, grease, pen marks, scuff marks, bugs and more ...**

### Features and Benefits:

- Lowers building maintenance costs.
- Extends the beauty and value of your property.
- Available in four gloss options in all standard colors.
- Offered on all AEP Span profiles (inquire for available lead times).
- 30 Year Limited Warranty.
- DuraPrep Prep 400 sold separately (see reverse for details).



## PROTECT YOUR INVESTMENT Offered on all AEP Span wall panels

**Oil Canning** : All flat metal surfaces can display waviness commonly referred to as "oil canning". "Oil canning" is an inherent characteristic of steel products, not a defect, and therefore is not a cause for panel rejection.

**800-733-4955** Contact your AEP Span Representative for more information.

[www.aepspan.com](http://www.aepspan.com)

# Graffiti-Resistant Coating System



Let AEP Span help protect your investment.



TEST	SPECIFICATION	RESULTS
<b>Dry Film Thickness</b> (nominal)	ASTM D5796	Standard Primer .15-.30mil Standard Topcoat .70-.80mil GR Clear .45-.55mil
<b>Gloss</b> 60° specular gloss	ASTM D523	Low Gloss Graffiti-Resistant Coating (10 - 15) Medium Gloss Graffiti-Resistant Coating (25 - 35) Medium Gloss Graffiti-Resistant Coating (50 - 70) High Gloss Graffiti-Resistant Coating (80+)
<b>Flexibility, T-bend</b>	ASTM D4145	0T – 1T; No pick-off
<b>Chemical Resistance</b>	ASTM D1308	10% Muriatic Acid, 15 minutes: No discoloration 25% NaOH, 1 hour: No effects
<b>Humidity</b>	ASTM D2247 ASTM D714	Passes 1,000 hours No #8 blisters. 100% relative humidity @ 95°F
<b>South Florida Exposure</b>	ASTM D2244	Maximum 5 NSB units color change, <0.01 mils/year film erosion



PPG Industries Graffiti-Resistant Clear Coating System meets or exceeds the American Architectural Manufacturers Association (AAMA) 2605 standards for performance and longevity.

DURAPREP® is a registered trademark of PPG Architectural Finishes, Inc.

**800-733-4955** Contact your AEP Span Representative for more information.

©2016 ASC Profiles LLC. All rights reserved. December 2016 (PS115) 300

[www.aepspan.com](http://www.aepspan.com)